

# SA516 GR. 60/70 ACC. TO ASME/

# SA516 GR. 60/70 ACC. TO ASTM

We keep the following steel grade in stock:

**SA516 Gr. 60/70 acc. to ASME /SA516 Gr. 60/70 acc. to ASTM**

This steel grade is produced for pressure vessels with low and middle working temperature.

Delivery with certificate 3.1 acc. to DIN EN 10204

The plates are additional tested with S5 (impact test at  $-50^{\circ}\text{C}$ )

## Chemical composition (heat analysis %)

Grade	C max.				Si	Mn		P, S max.
Thickness mm	$\leq 12,5$	$> 12,5$ $\leq 50,0$	$> 50,0$ $\leq 100,0$	$> 100,0$		$\leq 12,5$	$> 12,5$	
SA516 Gr.60	0,21	0,23	0,25	0,27	0,15 – 0,40	0,60 – 0,90	0,85 – 1,20	0,025
SA516 Gr. 70	0,27	0,28	0,30	0,31	0,15 – 0,40	0,85 – 1,20	0,85 – 1,20	0,025

## Mechanical properties in delivery condition

Tensile testing on transverse specimens at room temperature

Grade	R <sub>m</sub> (MPa)	R <sub>p0,2</sub> bzw. R <sub>t0,5</sub> (MPa) min.	A in % min. l <sub>0</sub> $\leq$ 50 mm	A in % min. l <sub>0</sub> $>$ 50 mm
SA516 Gr.60	415 – 550	220	25	21
SA516 Gr. 70	485 – 585	260	21	17

## Thickness/dimensions

Thickness: 5 - 250 mm/ dimensions: up to 4,000 mm. You get these plates with our special ANCOFER-Service. Please contact our sales department flame cut parts.

ANCOFER is certificated in conformity to DIN EN ISO 9001, to DIN EN 1090 and to DIN EN ISO 50001.

**ANCOFER STAHLHANDEL**

Rheinstraße 163

D-45478 Mülheim an der Ruhr

Telefon +49 208 5802-0

E-Mail [info@as.dillinger.biz](mailto:info@as.dillinger.biz)

[www.ANCOFER.de](http://www.ANCOFER.de)

**UNSER WORT IST STAHL.**

Competent and prompt response,  
from enquiry to delivery